



**THE RUSCOE
COMPANY**
Adhesives &
Sealants

RUSCOETHANE PITCH PAN

Two Part Polyurethane Pourable Sealer

Ruscoethane Pitch Pan Sealer is a versatile, two component pourable sealer, designed for predictable open-times that sets to a tough yet flexible seal.

Benefits

- Solvent free
- 100% Solids
- Fast green strength
- Excellent moisture resistance
- No VOC

Physical Properties

- | | |
|----------------|-----------------------------|
| • Viscosity | 50,000 - 75,000 cps (mixed) |
| • Total Solids | 100% |
| • Weight/gal | 13.0 (mixed) |
| • Color | Black/Gray |
| • Flash Point | None |
| • VOC | 0 gr/liter |
| • Open Time | 30-45 minutes @ 77° F |
| • Application | Pourable |
| • Shelf Life | 12 months, closed container |
| • Cure Time | 24 hours |

Mixing Instructions

Pour part "B" into part "A" and mix thoroughly until all streaks disappear and the two parts are uniform in color. The Part "B" pint can is pre-measured for the proper mix ratio to Part "A". Once completely mixed, pour immediately into the pitch pocket. Pitch pocket should be clean and dry when filled to prevent foaming. Make sure there is complete contact to all surfaces. Open time will vary slightly according to air and surface temperature and relative humidity.

Ruscoethane can be slightly sloped away from the stack within 30-45 minutes of mixing. This will ensure water run off to the edge of the pitch pocket.

Refer to MSDS prior to using Ruscoethane Pitch Pan Sealer.
Material Data Safety Sheet is available by calling 1-800-293-8148.

Legal: For your information

All statements, technical information and recommendations contained herein are based on tests believed to be reliable, but the accuracy or completeness is not guaranteed, and the following is made in lieu of all warranties expressed or implied. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of, or the inability to use the product. Before production, user shall determine the suitability of the product for their intended use and assumes all risk and liability in connection with and production.

The Ruscoe Company

P.O. Box 3858, Akron, Ohio 44314-0858 sales@ruscoe.com
485 Kenmore Blvd., Akron, Ohio 44301 • 330-253-8148 • 800-293-8148 • Fax: 330-253-2933