

TECHNICAL DATA SHEET



No. 383 HIGH TACK MASTIC ADHESIVE

DESCRIPTION

This heavy mastic adhesive is a rubber-resin formulation in a special solvent formulation. High Tack mastic adhesive is pressure sensitive so that it has instant grab on practically all surfaces used in construction.

SUGGESTED USES

This quick-tack, construction-grade adhesive will bond many special building and construction materials including DuPont Tyvek® Housewrap and polyethylene film to wood, steel, aluminum and concrete, or to one another. May be repositioned.



SURFACE PREPARATION AND APPLICATION

Bonding surfaces must be free of moisture, oils, dirt and other contaminants.

High Tack mastic may be applied by cartridge dispenser to a clean, dry surface; no thinning is required. Drying time is approximately 5 minutes for a surface skin, but adhesive bead remains tacky for about 14 days permitting easy repositioning as it will re-bond to itself. Fully cured within 14 days.

Open time exceeds 30 minutes, with wide temperature application range from 20°F to +100°F. Will also adhere to wet or frozen lumber.

STORAGE AND SHELF LIFE

Extremely flammable vapor; keep away from heat, sparks and open flame. The Ruscoe Company recommends storage in original, sealed container below 100°F.

HEALTH AND SAFETY

Health and safety data sheets available upon request at The Ruscoe Company. Contact with skin and eyes should be avoided and necessary protective equipment and clothing should be worn.

CLEANING

For cleanup use petroleum distillates.

TYPICAL PROPERTIES

Color	Tan
Solids, by Weight %	58-65%
Viscosity, Brookfield, Test Result, CPS (#7 @20 rpm)	45,000 – 60,000
Pounds Per Gallon @77°F (25°C)	7.0 – 7.4
Solvents	Hexane
Shelf Life	12 Months

All statements, technical information and recommendations contained herein are based on tests believed to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties expresses or implied.

Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss, or damage, direct or consequential, arising out of the use of, or the inability to use the product. Before using, user shall determine the suitability of the product for their intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing many are not changed except by an agreement signed by officers of seller or manufacturer.